

Data sheet Issue 03/2022

BYK-9730

Silicone and polymer-containing defoamer for all common base oils in industrial lubricant applications.

Product data

Composition Solution of a polyacrylate, containing silicone

Typical properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (68 °F): 6.43 lbs/US gal Solvents: Aromatic-free hydrocarbon Flash point: 108 °F

Applications

Lubricants and mold release

Special features and benefits

BYK-9730 is a versatile defoamer for lubricants. The additive is particularly suitable for the industrial lubricants sector and demonstrates excellent defoaming results in all common base oils, such as mineral oils, polyalphaolefins, naphthenic oils, and ester oils. The targeted combination of active substances ensures BYK-9730 defoams with the greatest efficiency even at low concentrations, and is simultaneously very compatible in the base oil at high concentrations. The additive thereby exhibits good long-term defoaming in the finished product after storage and has no negative impact on the transparency of the oils.

Recommended use

Mineral oils (API I-III)	
Polyalphaolefins	
Naphthenic oils	
Ester oils	

especially recommended recommended

Recommended levels

0.05–0.1 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. The optimum dosage should be determined by application-related test series.

Incorporation and processing instructions

The additive is stirred into the base oil before other components are added.

BYK-9730

Data sheet Issue 03/2022





BYK USA Inc. 524 South Cherry Street P.O. Box 5670 Wallingford, CT 06492 USA Tel 203 265-2086 Fax 203 284-9158

cs.usa@byk.com www.byk.com ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-MAX®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERBYK®, DISPERBYAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGL®, POLYAD®, PRIEX®, PURE THIX®, RECYCLOBLEND®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25° **are registered trademarks of the BYK group.**

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions.