



CERECLOR

GRADE: 'CERECLOR' 42

SPEC REF: S/CER 42

DATE: 10/10/2001

CERECLOR Sales - Generic Specification

APPEARANCE

Clear mobile liquid free from visible foreign matter . Test method - Visual inspection

SPECIFICATION DETAILS

Analyte	Units	Lower Limit	Upper Limit	Method / Comments
Colour	Hazen		350	Test Method ASTM D1209
Density at 25°C	g/ml	1.140	1.175	Test Method ASTM D4052
Viscosity at 25°C	poise	14	30	Test Method ASTM D445
Total Chlorine	% w/w	41	44	Test Method MB 005

Additional Comments

Product description: C₂₂₋₃₀ chlorinated paraffin

QA Status

INOVYN ChlorVinyls' CERECLOR™ manufacturing sites are registered to ISO9001 & ISO14001.

INOVYN ChlorVinyls Limited
Runcorn Site HQ
South Parade
PO Box 9
Runcorn
Cheshire WA7 4JE
United Kingdom

INOVYN™ is a trademark of INOVYN ChlorVinyls Limited.

The BUBBLE Logo™, CERECLOR™, CHLOROS™, EVIPOL™, GENKLENE™, MEFLEX™, METHOKLONE™, PERSTABIL™, SODAGRAN™, SODASTRAW™, SOLTENE™ and SOLVE-CARE™ are trademarks of INOVYN ChlorVinyls Limited.

NORVINYL™ and PEVIKON™ are trademarks of INOVYN ChlorVinyls Limited and/ or INOVYN Newton Aycliffe Limited.

KERLING™ and the K Logo™ are trademarks of INOVYN ChlorVinyls Limited/ Polymer Holdings AS/ Kerling Pic.
SOLVIN® is a trademark of Solvay SA and is licensed to INOVYN for use.
VINYLOOP® is a trade mark, the property of Vinyloop Ferrara S.p.a.



'CERECLOR' 42.pdf